

1-34. (Cancelled)

35. (Currently amended) A bioerodible implant for treating an inflammation-mediated condition of an eye in an individual, the implant consisting essentially of a steroidal anti-inflammatory agent and a bioerodible copolymer, the implant structured to be placed in the vitreous of the eye by being an extruded filament, the implant having a weight between ~~about~~ 500 µg and ~~about 1100~~ 1000 µg and releasing at least about 20% of the agent within about 20 days in vitro.

36. (Cancelled)

37. (Previously amended) The bioerodible implant according to claim 35, wherein the steroidal anti-inflammatory agent is selected from the group consisting of cortisone, dexamethasone, hydrocortisone, methylprednisolone, prednisolone, prednisone, triamcinolone and mixtures thereof.

38. (Previously amended) The bioerodible implant according to claim 35, wherein the steroidal anti-inflammatory agent is dexamethasone.

39. (Previously amended) The bioerodible implant according to claim 35, wherein the implant releases at least about 30% of the agent after about 20 days in vivo.

40 and 41. (Canceled)

42. (Previously amended) The bioerodible implant according to claim 35, wherein the steroidal anti-inflammatory agent comprises about 50 to about 80 weight percent of the implant.

43. (Previously amended) The bioerodible implant according to claim 42, wherein the steroidal anti-inflammatory agent comprises about 70% by weight of the implant.

44. (Previously amended) The bioerodible implant according to claim 35, wherein the bioerodible copolymer is a polyester.

45. (Previously amended) The bioerodible implant according to claim 44, wherein the bioerodible copolymer is polylactic acid polyglycolic acid (PLGA) copolymer.

46. (Previously amended) The bioerodible implant according to claim 35, wherein the condition of the eye to be treated is selected from the group consisting of uveitis, macular edema, macular degeneration, retinal detachment, ocular tumors, fungal infections, viral infections, multifocal choroiditis, diabetic uveitis, proliferative vitreoretinopathy (PVR), sympathetic ophthalmia, Vogt Koyanagi-Harada (VKH) syndrome, histoplasmosis, and uveal diffusion.

47. (Previously amended) The bioerodible implant according to claim 46, wherein the condition of the eye to be treated is uveitis.

48.-50. (Canceled)

51. (Previously amended) The bioerodible implant according to claim 35, wherein the individual whose eye is to be treated is a human.

52. (Currently amended) An implant for treating an inflammation-mediated condition of the eye in an individual, the implant consisting essentially of a solid body with particles of a steroidal anti-inflammatory agent entrapped within a bioerodible copolymer, the body structured for placement into the vitreous of the eye by being an extruded filament, the solid body having a weight between about

500 µg and ~~about 1100~~ 1000 µg and releasing at least about 30% of the agent within about 20 days in vitro.

53.-92. (Cancelled)

93. (Currently amended) A bioerodible implant for treating an inflammation mediated condition of the eye in an individual, the implant consisting of an anti-inflammatory agent and a bioerodible copolymer, the implant structured to be placed in the vitreous of the eye by being an extruded filament, the implant having a weight between ~~about 500 µg pg~~ and 1000 µg ~~about 1100 pg~~ and releasing at least about 20% of the agent within about 20 days in vitro.

94. (Currently amended) A bioerodible implant for treating an inflammation mediated condition of the eye in an individual, the implant consisting of a solid body with particles of a steroidal anti-inflammatory agent entrapped within a bioerodible copolymer, the implant structured to be placed in the vitreous of the eye by being an extruded filament, the implant having a weight between ~~about 500 ug pg~~ and 1000 ug ~~about 1100 pg~~ and releasing at least about 20% of the agent within about 20 days in vitro.

Claim 95. (Cancelled)

Claim 96 (New) The implant of claim 93 wherein said filament has a diameter of between 650 and 790 nm. and a length of between 0.94 and 1.97 µm.

Claim 97 (New) The implant of claim 94 wherein said filament has a diameter of between 650 and 790 nm. and a length of between 0.94 and 1.97 µm.